CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST REPORT OF CEMENT CONCRETE KERB STONE

Lab ID : **CP-2017-05-06-02** **Date: 12-05-17**

Customer : Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.

Address : (Project Division), Yelahanka Zone, BBMP, Bangalore.

Project Name : Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03

Agency : Technical Manager(West), KRIDL, Banagalore.

Customer's Reference : EE(Project)Ynk Zone/WO/02/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 06-05-17

Sample ID No : 2017-05-06-02/01

Sample Type /Size : CC Kerb Stone/ 450*165*400mm

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 06/05/2017

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	Kg	(Sq.mm)	(KN)	(N/mm2)	(N/mm2)	(N/mm2)
1	A	100.01	165.51	2.864	7854	151.0	19.2	17.9	22.3
2	B	100.03	165.49	2.741	7857	150.7	19.2	19.2	24.0
3	C	100.01	165.50	2.849	7854	149.7	19.1	19.1	23.8

Note:
The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

50

CEMENT CONCRETE FLOORING TILES

Lab ID	:	**CP-2017-05-06-02** **Date: 10-05-17**
Customer	:	Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.
Address	:	(Project Division), Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03
Agency	:	Technical Manager(West), KRIDL, Banagalore.
Customer Reference	:	EE(Project)Ynk Zone/WO/02/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-05-17
Sample ID No	:	2017-05-06-02/02
Sample Type/ Size	:	Pre-Polished Designer Cement Concrete Tiles
Reference to BIS codes	:	IS 1237:2012
Date of test	:	06-05-17

1.Wet Transverse Strength

Sl.No.	Dimension (mm)			Wet Transverse Strength	Average	Requirement as per IS:1237-2012
	L	B	T	(N/mm^2)	(N/mm^2)	
1	400	400	25.17	7.82	7.78	The average wet transverse strength shall not be less than $3N/mm^2$.
2	400	400	25.42	8.10		
3	400	400	25.05	7.40		
4	400	400	25.19	7.88		
5	400	400	25.22	8.10		
6	400	400	25.25	7.40		

2. Water Absorption

Sl.No.	Dimension (mm)			Water Absorption	Average	Requirement as per IS:1237-2012
	L	B	T	(%)	(%)	
1	400	400	25.05	3.17	3.84	The average percentage of water absorption shall not exceed 10.
2	400	400	25.17	3.22		
3	400	400	25.06	4.19		
4	400	400	25.16	4.17		
5	400	400	25.08	3.98		
6	400	400	25.11	4.32		

AE

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID : **CP-2017-05-02-03** **Date: 03-05-2017**

Customer : Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.

Address : (Project Division), Yelahanka Zone, BBMP, Bangalore.

Project Name : Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03

Agency : Technical Manager(West), KRIDL, Banagalore.

Customer's Reference : EE(Project)Ynk Zone/WO/02/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 02-05-17

Sample ID No : 2017-05-02-03/01

Sample Type : Zuari 53grade

Reference to BIS codes :
IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,
IS 4031 (Part 1,2 3,4,5, 6,11):1988
IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4
IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5
IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6
IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5
IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5
IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6

Date of test : 02-05-17

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	3.98	–
2	Finess by Air permeablity method (m^2/kg, Min)	292.5	225m^2/kg, Min
3	Density (gm/cc)	3.22	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	215 minutes	Not less than 30 minutes
6	Final Setting time	290 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

(43)

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID : **CP-2017-05-02-03** **Date: 30-05-2017**

Customer : Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.

Address : (Project Division), Yelahanka Zone, BBMP, Bangalore.

Project Name : Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03

Agency : Technical Manager(West), KRIDL, Banagalore.

Customer's Reference : EE(Project)Ynk Zone/WO/02/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 02-05-17

Sample ID No : 2017-05-02-03/01

Sample Type : Zuari 53grade

Reference to BIS codes : IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,
IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5
IS 4031 Part 6, Determination of Compressive Strength, Clause 6

Date of test : 02-05-17

Compressive Strength			
Sl.No.	**Physical properties**	**Results**	**Requirement as per IS 12269: 2013**
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	55.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE

Prepared by
Harshitha

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-05-02-03** **Date: 06-05-2017**
Customer	:	Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.
Address	:	(Project Division), Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03
Agency	:	Technical Manager(West), KRIDL, Banagalore.
Customer's Reference	:	EE(Project)Ynk Zone/WO/02/2017-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	02-05-17
Sample ID No	:	2017-05-02-03/02(b)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	02-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	729	729	4.9	95.1	90-100
3	20 mm	6998	7727	51.5	48.5	30-70
4	10 mm	4122	11849	79.0	21.0	10-35
5	4.75 mm	2896	14745	98.3	1.7	0-5
6	Pan	255	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

146

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-02-03** **Date: 06-05-2017**

Sample ID No : 2017-05-02-03/02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	10.5	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.9	
3	Specific Gravity	2.64	–
4	Bulk Density(Loose) (Kg/l)	1.51	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.27	–

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AE

****End of Report****

145

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-05-02-03** **Date: 06-05-2017**
Customer	:	Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.
Address	:	(Project Division), Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03
Agency	:	Technical Manager(West), KRIDL, Banagalore.
Customer Reference	:	EE(Project)Ynk Zone/WO/02/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	02-05-17
Sample ID No	:	2017-05-02-03/02(a)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	02-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	72	72	1.4	98.6	90-100
3	10 mm	3592	3664	73.3	26.7	25-55
4	4.75 mm	1102	4766	95.3	4.7	0-10
5	Pan	234	5000	100	0	_

AE

CIVIL PRO Sig..... Date..... BANGALORE

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-02-03** **Date: 06-05-2017**

Sample ID No : 2017-05-02-03/02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	14.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.6	
3	Specific Gravity	2.61	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.56	–
6	Water Absorption(%)	0.25	–
7	Aggregate crushing Value(%)	24.5	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	21.8	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2017-05-02-03** **Date: 06-05-17**
Customer	:	Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.
Address	:	(Project Division), Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03
Agency	:	Technical Manager(West), KRIDL, Banagalore.
Customer's Reference	:	EE(Project)Ynk Zone/WO/02/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	02-05-17
Sample ID No	:	2017-05-02-03/03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	02-05-17
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0	100	100	100	100	100
2	4.75 mm	49	49	4.9	95.1	90-100	90-100	90-100	95-100
3	2.36 mm	126	175	17.5	82.5	60-95	75-100	85-100	95-100
4	1.18 mm	215	390	39	61	30-70	55-90	75-100	90-100
5	600 micron	222	612	61.2	38.8	15-34	35-59	60-79	80-100
6	300 micron	301	913	91.3	8.7	5-20	8-30	12-40	15-50
7	150 micron	50	963	96.3	3.7	0-10	0-10	0-10	0-15
8	Pan	37	1000	100	0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL PRO BANGALORE Sig..... Date.....

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2017-05-02-03** **Date: 06-05-17**

Sample ID No : 2017-05-02-03/03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	2.05	_
2	Specific Gravity	2.54	_
3	Material finer than 75 micron(%)	4.0	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-05-15-10** **Date: 19-05-17**

Customer : Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.

Address : (Project Division), Yelahanka Zone, BBMP, Bangalore.

Project Name : Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03

Agency : Technical Manager(West), KRIDL, Banagalore.

Customer's Reference : EE(Project)Ynk Zone/WO/02/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-05-17

Sample ID No : 2017-05-15-10/01

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/05/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	12/05/2017	19/05/2017	150.11 X 150.48 X 150.39	22589	8.175	386.3	17.1	17.5
2	PCC	M20	12/05/2017	19/05/2017	150.24 X 150.39 X 149.87	22595	8.168	404.4	17.9	
3	PCC	M20	12/05/2017	19/05/2017	150.64 X 150.79 X 150.65	22715	8.117	397.5	17.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-05-15-10** **Date: 09-06-17**

Customer : Assistant Executive Engineer, (Project Division), Yelahanka Zone, BBMP, Bangalore.

Address : (Project Division), Yelahanka Zone, BBMP, Bangalore.

Project Name : Providing Children Play Equipment and open gym equipment at SFS 208 Park Opposite to Mother Dairy Ward No.03

Agency : Technical Manager(West), KRIDL, Banagalore.

Customer's Reference : EE(Project)Ynk Zone/WO/02/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-05-17

Sample ID No : 2017-05-15-10/01

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/06/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	12/05/2017	09/06/2017	150.35 X 151.01 X 150.68	22704	8.198	538.1	23.7	23.3
2	PCC	M20	12/05/2017	09/06/2017	150.74 X 150.33 X 150.47	22661	8.165	530.3	23.4	
3	PCC	M20	12/05/2017	09/06/2017	149.87 X 150.68 X 151.01	22582	8.146	517.1	22.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****